Of totems in App. No. 10/521,060 Amendment dated November 21, 2006 Reply to Office action of August 21, 2006

## **Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the present application.

## **Listing of Claims:**

Claim 1 (currently amended): A method of manufacturing a crystal of a group III-V compound, the method comprising:

a deposition step of depositing a metal film on a substrate;

a heat-treatment step of heat-treating the metal film under an atmosphere in which a metal-film patterning compound is present so that the metal film becomes patterned with a plurality of holes or grooves having an indefinite shape; and

a growth step of growing a group III-V crystal on the post-heat-treated metal film.

Claim 2 (currently amended): A method of manufacturing a crystal of a group III-V compound, the method comprising:

a deposition step of depositing a metal film on a substrate;

a heat-treatment step of heat-treating the metal film under an atmosphere in which a metal-film patterning compound is present so that the metal film becomes patterned with a plurality of holes or grooves having an indefinite shape;

a first growth step of growing a group III-V compound buffer film on the postheat-treated metal film; and

a second growth step of growing a group III-V crystal on the group III-V compound buffer film.

Claim 3 (currently amended): A group III-V crystal manufacturing method as set forth in claim 1, wherein:

the holes or grooves formed in the metal film in said heat-treatment step have an average width of 2 nm to 5000 nm; and

Of totems in App. No. 10/521,060 Amendment dated November 21, 2006 Reply to Office action of August 21, 2006

the aperture fraction, being the percentage of the surface area that the holes or grooves occupy with respect to the substrate total surface area, is 5% to 80%.

Claim 4 (previously presented): A group III-V crystal manufacturing method as set forth in claim 1, characterized in that the substrate is silicon, sapphire, SiC, ZrB<sub>2</sub>, or a group III-V compound.

Claim 5 (previously presented): A group III-V crystal manufacturing method as set forth in claim 1, characterized in that the metal film contains titanium or vanadium.

Claim 6 (previously presented): A group III-V crystal manufacturing method as set forth in claim 1, wherein the method renders the thickness of the metal film to be 10 nm to 100 nm.

Claim 7 (previously presented): A group III-V crystal manufacturing method as set forth in claim 1, characterized in that the heat treatment is carried out at 800°C to 1200°C for 0.5 minutes to 20 minutes.

Claim 8 (previously presented): A group III-V compound crystal manufactured by a group III-V crystal manufacturing method as set forth in claim 1.

Claim 9 (previously presented): A group III-V compound crystal as set forth in claim 8, wherein the group III-V crystal is  $Ga_xAl_yIn_{1-x-y}$  ( $0 \le x \le 1$  and  $0 \le y \le 1$ ).

Claim 10 (currently amended): A group III-V crystal manufacturing method as set forth in claim 2, wherein:

the holes or grooves formed in the metal film in said heat-treatment step have an average width of 2 nm to 5000 nm; and

Of totems in App. No. 10/521,060 Amendment dated November 21, 2006 Reply to Office action of August 21, 2006

the aperture fraction, being the percentage of the surface area that the holes or grooves occupy with respect to the substrate total surface area, is 5% to 80%.

Claim 11 (previously presented): A group III-V crystal manufacturing method as set forth in claim 2, characterized in that the substrate is silicon, sapphire, SiC, ZrB<sub>2</sub>, or a group III-V compound.

Claim 12 (previously presented): A group III-V crystal manufacturing method as set forth in claim 2, characterized in that the metal film contains titanium or vanadium.

Claim 13 (previously presented): A group III-V crystal manufacturing method as set forth in claim 2, wherein the method renders the thickness of the metal film to be 10 nm to 100 nm.

Claim 14 (previously presented): A group III-V crystal manufacturing method as set forth in claim 2, characterized in that the heat treatment is carried out at 800°C to 1200°C for 0.5 minutes to 20 minutes.

Claim 15 (previously presented): A group III-V compound crystal manufactured by a group III-V crystal manufacturing method as set forth in claim 2.

Claim 16 (previously presented): A group III-V compound crystal as set forth in claim 15, wherein the group III-V crystal is  $Ga_xAl_yIn_{1-x-y}$  ( $0 \le x \le 1$  and  $0 \le y \le 1$ ).